

LIST OF FIGURES

S. No.	Title	Page No.
1	Image represents the monotrichous flagellum of <i>Pseudomonas aeruginosa</i>	07
2	Schematic diagram of Energy band for semiconductors	13
3	Schematic representation of isolation and separation of bacterial nanowires for the electrochemical applications	23
4	Schematic representation of metal oxide nanoparticles (CuO, NiO and ZnO) coated bacterial nanowires for the electrochemical applications	25
5	AFM images of bacterial nanowires for various growth phase conditions: (a) Log phase, (b) stationary phase	36
6	Separation of bacterial nanowires images of <i>P. aeruginosa</i> bacteria using various shearing phase and growth conditions methods: (a) sonicator, Log phase, (b) sonicator stationary phase, (c) Magnetic stirrer, log phase and (d) Magnetic stirrer, stationary phase	38
7	Roughness of the (a) log phase bacterial nanowires (b) stationary phase bacterial nanowires	39
8	HR-TEM images of the bacterial nanowires from <i>P. aeruginosa</i>	40
9	CVs of the bare glassy carbon electrode (a) and bacterial nanowire modified glassy carbon electrode (b) recorded in 0.1M H ₂ SO ₄ , at a scan range of 20 mVs ⁻¹	42
10	LSV curve for bacterial nanowires (black curve) and ZnO nanoparticles coated bacterial nanowires (red curve) recorded in 0.1M H ₂ SO ₄ , at a scan range of 20 mVs ⁻¹	44
11	EIS recorded for the absence (blank) and presence of bacterial nanowires on to the electrode in 1 mM of K ₃ Fe(CN) ₆ in 0.1 M KCl	47
12	Absorption spectra obtained for the CuO nanoparticles	49
13	Absorption spectra obtained for the NiO nanoparticles	49
14	Absorption spectra obtained for the ZnO nanoparticles	50

15	FT-IR spectrum of the CuO nanoparticles	52
16	FT-IR spectrum of the NiO nanoparticles	53
17	FT-IR spectrum of the ZnO nanoparticles	53
18	XRD pattern of the CuO nanoparticles	55
19	XRD pattern of the NiO nanoparticles	56
20	XRD pattern of the ZnO nanoparticles	56
21	AFM images recorded for the CuO nanoparticles (a) 2D image, (b) 3D image and (c) roughness of CuO nanoparticles	58
22	AFM images recorded for the NiO nanoparticles (a) 2D image, (b) 3D image and (c) roughness of CuO nanoparticles	59
23	AFM images recorded for the ZnO nanoparticles (a) 2D image, (b) 3D image and (c) roughness of CuO nanoparticles	60
24	SEM images of the CuO Nanoparticles with different magnifications (a-d)	62
25	SEM images of NiO Nanoparticles with low (a) and high magnifications (b)	63
26	SEM images of ZnO Nanoparticles with low (a) and high magnifications (b)	63
27	HR-TEM images of CuO nanoparticles with different magnifications (a-d)	65
28	HR-TEM images of NiO nanoparticles with different magnifications (a-c)	66
29	HR-TEM images of ZnO nanoparticles with different magnifications (a-d)	67
30	HR-TEM images of the CuO nanoparticles coated upon the bacterial nanowires at different magnifications	69
31	HR-TEM images of the NiO nanoparticles coated upon the bacterial nanowires at different magnifications	69
32	HR-TEM images of the ZnO nanoparticles coated upon the bacterial nanowires at different magnifications	70
33	CVs of the bacterial nanowires modified glassy carbon electrode (a) and CuO nanoparticles coated bacterial nanowires modified glassy carbon electrode (b) recorded in 0.1M H ₂ SO ₄ , at a scan rate of 20 mVs ⁻¹	73

34	CVs of the bacterial nanowires modified glassy carbon electrode (a) and NiO nanoparticles coated bacterial nanowires modified glassy carbon electrode (b) recorded in 0.1M H ₂ SO ₄ , at a scan rate of 20 mVs ⁻¹	74
35	CVs of the bacterial nanowires modified glassy carbon electrode (a) and CuO nanoparticles coated bacterial nanowires modified glassy carbon electrode (b) recorded in 0.1M H ₂ SO ₄ , at a scan rate of 20 mVs ⁻¹	75
36	LSV curve for bacterial nanowires (a) and CuO nanoparticles coated bacterial nanowires (b) recorded in 0.1M H ₂ SO ₄ , at a scan rate of 20 mVs ⁻¹	78
37	LSV curve for bacterial nanowires (a) and NiO nanoparticles coated bacterial nanowires (b) recorded in 0.1M H ₂ SO ₄ , at a scan rate of 20 mVs ⁻¹	79
38	LSV curve for bacterial nanowires (a) and ZnO nanoparticles coated bacterial nanowires (b) recorded in 0.1M H ₂ SO ₄ , at a scan range of 20 mVs ⁻¹	80
39	EIS recorded for bacterial nanowires (a) CuO nanoparticles coated bacterial nanowires (b). Redox analyte was 1 mM of K ₃ Fe(CN) ₆ in 0.1M KCl. The electrode was polarized at 0.25 V and the frequency range was 1 Hz to 100 kHz	86
40	EIS record for bacterial nanowires (a) NiO nanoparticles coated bacterial nanowires (b). Redox analyte was 1 mM of K ₃ Fe(CN) ₆ in 0.1M KCl. The electrode was polarized at 0.25 V and the frequency range was 1 Hz to 100 kHz	87
41	EIS recorded for bacterial nanowires (a) ZnO nanoparticles coated bacterial nanowires (b). Redox analyte was 1 mM of K ₃ Fe(CN) ₆ in 0.1M KCl. The electrode was polarized at 0.25V and the frequency range was 1 Hz to 100 kHz	88

LIST OF TABLES

S. No.	Title	Page No.
1	List of the impedance components for the blank, bacterial nanowires and metal oxide nanoparticles coated bacterial nanowires thin film by fitting the experimental data.	89

Abstract