

## CONTENTS FOR TABLES

		Page No.
1.1.	Chemical composition of some common manganese minerals.	4
1.2.	Primary production of manganese by area.	5
1.3.	The use of manganese in steel industry.	11
1.4.	Representative manganese compounds.	17
1.5.	Important Mn(II) compounds and their properties.	19
1.6.	Physical Properties of Manganese(III) Compounds.	22
1.7.	Manganese dioxide Crystal Phases.	26
1.8.	Physical properties of Mn(V) compounds.	35
1.9.	Physical properties of Mn(VI) compounds.	35
1.10.	Some of the Mn(VII) compounds and their physical properties.	37
3.1.	Physicochemical properties of manganese effluent.	62
3.2.	%MnO <sub>2</sub> in fused MnCO <sub>3</sub> alone.	68
3.3.	%MnO <sub>2</sub> composition in MnCO <sub>3</sub> fused material with variable quantity of Na <sub>2</sub> CO <sub>3</sub> , fusion temperature and time.	72
3.4.	%MnO <sub>2</sub> in MnCO <sub>3</sub> after fusion with Na <sub>2</sub> CO <sub>3</sub> at high weight ratio, CaCO <sub>3</sub> and MgCO <sub>3</sub> for 2.5 h at 450 °C.	75
3.5.	%MnO <sub>2</sub> in fused MnCO <sub>3</sub> material with variable quantity of NaOH, temperature and time.	82
4.1.	The prices as provided by M/s Atul Ltd. Valsad as of various chemicals employed in the manganese recovery are as below.	115
4.2.	Approximate cost calculations for the preparation of one kg MnCO <sub>3</sub> from ME.	115
4.3.	Approximate cost calculations for the preparation of one kg α-MnO <sub>2</sub> by fusion with 3.95 times Na <sub>2</sub> CO <sub>3</sub> .	118
4.4.	Approximate cost calculations for the preparation of one kg γ-MnO <sub>2</sub> by fusion with 3.95 times Na <sub>2</sub> CO <sub>3</sub> .	119
4.5.	Approximate cost calculations for the preparation of one kg α-MnO <sub>2</sub> by chemical oxidation with sodium bromate in strongly acidic solutions.	121
4.6.	Approximate cost calculations for the preparation of one kg α-MnO <sub>2</sub> by chemical oxidation with KMnO <sub>4</sub> in moderately strongly acidic solutions.	122

## CONTENTS FOR PROCESS FLOW DIAGRAMS

		Page No.
3.1	Manganese precipitation as $\text{MnCO}_3$ from its acid effluent at pH 2	66
3.2	Manganese recovery as 55-64% $\text{MnO}_2$ from its acid effluent <i>via</i> $\text{MnCO}_3$ (pH 2) fusion with none.	67
3.3	A) Manganese recovery as 75.62% $\text{MnO}_2$ from its acid effluent <i>via</i> $\text{MnCO}_3$ fusion with $\text{Na}_2\text{CO}_3$ at low weight ratio	72
	B) Showing different stages during Manganese recovery as 70-76% $\text{MnO}_2$ from its acid effluent <i>via</i> $\text{MnCO}_3$ fusion with $\text{Na}_2\text{CO}_3$ at low weight ratio.	73
3.4	Manganese recovery as 71-93% $\text{MnO}_2$ from its acid effluent <i>via</i> $\text{MnCO}_3$ fusion with $\text{Na}_2\text{CO}_3$ at high molar ration.	76
3.5	Manganese recovery as 45-73% $\text{MnO}_2$ from its acid effluent <i>via</i> $\text{MnCO}_3$ (pH 2) fusion with NaOH.	81
3.6	Manganese extraction as $\text{MnO}_2$ by chlorine gas.	87
3.7	Manganese extraction as $\text{MnO}_2$ by $\text{NaBrO}_3$ with as such effluent.	91
3.8	Manganese extraction as $\text{MnO}_2$ by $\text{NaBrO}_3$ at pH 2.	93
3.9	Manganese extraction as $\text{MnO}_2$ from as such effluent using $\text{KMnO}_4$	95
3.10	Manganese extraction as $\text{MnO}_2$ by potassium chlorate treatment on fused $\text{MnCO}_3$ .	97
3.11	Manganese extraction as $\text{MnO}_2$ by $\text{HNO}_3$ treatment on fused $\text{MnCO}_3$ .	100
3.12	Manganese extraction as $\text{MnO}_2$ by Ozone treatment on fused $\text{MnCO}_3$ .	102
3.13	Manganese extraction as $\text{MnO}_2$ by electrochemical oxidation at pH 2.	105
3.14	Manganese extraction as $\text{MnO}_2$ by electrochemical oxidation in acidic medium	105

## CONTENTS FOR DATA SHEETS

		Page No.
3.1.	Peak search and intensity data of XRD of Pyrolusite ore containing with 85% MnO <sub>2</sub> used in their dye manufacture by M/s Atul Ltd.	132
3.2.	(a). Peak search and intensity data of XRD of MnCO <sub>3</sub> sample fused at 450 °C for 4 h containing 58.45% MnO <sub>2</sub>	133
	(b). Peak search and intensity data of XRD of MnCO <sub>3</sub> sample fused at 450 °C for 6 h containing 53.89% MnO <sub>2</sub> .	134
	(c). Peak search and intensity data of XRD of MnCO <sub>3</sub> sample fused at 450 °C for 2.5 h containing 84% MnO <sub>2</sub> after HCl treatment.	135
3.3.	(a). Peak search and intensity data of XRD of MnCO <sub>3</sub> fused sample along with 1 g Na <sub>2</sub> CO <sub>3</sub> at 500 °C for 3 h sample containing 73.66% MnO <sub>2</sub> .	136
	(b). Peak search and intensity data of XRD of MnCO <sub>3</sub> fused sample along with 1.93 g Na <sub>2</sub> CO <sub>3</sub> at 500 °C for 3 h containing 73.88% MnO <sub>2</sub>	136
	(c). Peak search and intensity data of XRD of MnCO <sub>3</sub> fused sample along with 3.9 g Na <sub>2</sub> CO <sub>3</sub> at 500 °C for 3 h containing 75.40% MnO <sub>2</sub>	137
3.4.	(a). Peak search and intensity data of XRD of MnCO <sub>3</sub> sample fused along with 5 g Na <sub>2</sub> CO <sub>3</sub> at 450 °C for 2.5 h.	137
	(b). Peak search and intensity data of XRD of MnCO <sub>3</sub> sample fused along with 10 g Na <sub>2</sub> CO <sub>3</sub> at 450 °C for 2.5 h.	138
	(c). Peak search and intensity data of XRD of MnCO <sub>3</sub> sample fused along with 15 g Na <sub>2</sub> CO <sub>3</sub> at 450 °C for 2.5 h.	138
	(d). Peak search and intensity data of XRD of MnCO <sub>3</sub> sample fused along with 20 g Na <sub>2</sub> CO <sub>3</sub> at 450 °C for 2.5 h.	139
3.5.	(a) Peak search and intensity data of XRD of MnCO <sub>3</sub> sample fused along with 2 g CaCO <sub>3</sub> at 450 °C for 2.5 h.	140
	(b). Peak search and intensity data of XRD of MnCO <sub>3</sub> sample fused along with 2 g MgCO <sub>3</sub> at 450 °C for 2.5 h.	140
3.6.	(a). Peak search and intensity data of XRD of MnCO <sub>3</sub> fused sample at 450 °C along with 0.1 g NaOH for 2 h having 59.75% MnO <sub>2</sub> .	141
	(b). Peak search and intensity data of XRD of MnCO <sub>3</sub> fused sample at 450 °C along with 1.0 g NaOH for 3 h having 69.10% MnO <sub>2</sub> .	141
	(c). Peak search and intensity data of XRD of MnCO <sub>3</sub> fused sample at 450 °C along with 1.0 g NaOH for 4 h having 61.27% MnO <sub>2</sub> .	142
3.7.	Peak search and intensity data of XRD of 55.5% MnO <sub>2</sub> obtained by the chemical oxidation of Mn(II) in ME using Cl <sub>2</sub> gas.	142
3.8.	Peak search and intensity data of XRD of 88% MnO <sub>2</sub> obtained by the	143

- chemical oxidation of Mn(II) in ME using  $\text{NaBrO}_3$ .
- 3.9. Peak search and intensity data of XRD of 80%  $\text{MnO}_2$  obtained by the 144  
chemical oxidation of Mn(II) in ME using  $\text{KMnO}_4$ .
- 3.10. Peak search and intensity data of XRD of 72.14%  $\text{MnO}_2$  obtained by the 145  
chlorate treatment on fused  $\text{MnCO}_3$ .
- 3.11. Peak search and intensity data of XRD of 80.60%  $\text{MnO}_2$  obtained by 145  
 $\text{HNO}_3$  treatment on fused  $\text{MnCO}_3$ .
- 3.12. Peak search and intensity data of XRD of 74%  $\text{MnO}_2$  obtained by the 146  
ozone treatment on fused  $\text{MnCO}_3$ .

**CONTENTS FOR ANNEXURES**

	<b>Page No.</b>
<b>I</b> Suggested electrochemical regeneration of $\text{NaBrO}_3$	147
<b>II</b> Suggested chemical regeneration of $\text{NaBrO}_3$ with $\text{Cl}_2$ gas	148